

TEST REPORT

APPLICANT : Baoni International Inc.

ADDRESS : 3990 Bridlewood Drive Duluth, GA 30096, USA

SAMPLE DESCRIPTION : Block Rocks

COUNTRY TO IMPORT : USA

AGE REQUESTED ON APPLICATION FORM : 4+

LABELED AGE GRADE : Ages 4+

AGE GRADE APPLIED IN TESTING : Over 4 Years

SAMPLE RECEIVED DATE : 21-Nov-2018

SAMPLE RESUBMISSION DATE : 03-Dec-2018

TURN AROUND TIME : 21-Nov-2018 to 05-Dec-2018


The following test item(s) was/were performed on submitted sample(s) and/or component(s) confirmed by applicant

| TEST REQUESTED | TEST METHOD/REGULATION | RESULT |
|---|------------------------------|--------|
| Mechanical and Physical Properties | ASTM F963-17 | Pass |
| Flammability of Toys | ASTM F963-17 | Pass |
| Heavy Metals | ASTM F963-17 | Pass |
| Total Lead Content in Paint / Surface Coating | US CPSIA, Section 101 | Pass |
| Total Lead Content in Substrate | US CPSIA, Section 101 | Pass |
| Total Lead Content | US California Proposition 65 | Pass |
| Phthalates Content | US CPSIA, Section 108 | Pass |
| Phthalates Content | US California Proposition 65 | Pass |

Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to info.sh@eurofins.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to chinacomplaint@eurofins.com and referring to this report number.

Eurofins (Shanghai) contact informationCustomer service: VivianYang@eurofins.com / 021-36202898Sales specialist: JackZhang@eurofins.com / 18601770010

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins Product Testing Service (Shanghai) Co., Ltd

Joyce Liu
Lab Manager

SAMPLE PHOTO



EFSH18111740-CG-01

TO BE CONTINUED

COMPONENT LIST

| Component No. | Component |
|---------------|--|
| 1 | Green coating on wood |
| 2 | Orange coating on wood |
| 3 | Yellow coating on wood |
| 4 | Purple coating on wood |
| 5 | Dark blue coating on wood |
| 6 | Black coating on metal |
| 7 | White paper with multi-color coating (poker) |
| 8 | Red plastic |
| 9 | Black plastic zipper teeth |
| 10 | Transparent plastic film with underlying coating and paper |
| 11 | Black elastic excluding fabric |
| 12 | Black foam |
| 13 | Black fabric handle |
| 14 | Blue fabric body |
| 15 | Blue fabric lining |
| 16 | Black fabric zipper tape |
| 17 | Black fabric piping (lining) |
| 18 | Black fabric excluding elastic |
| 19 | Yellow embroidered threads |
| 20 | Black embroidered threads |
| 21 | Red embroidered threads |
| 22 | Blue embroidered threads |
| 23 | Purple embroidered threads |
| 24 | Green embroidered threads |
| 25 | White embroidered threads |
| 26 | Natural color wood excluding coating |
| 27 | Silver metal excluding coating (zipper slider) |
| 28 | Silver metal excluding coating (zipper puller) |
| 29 | Silver metal body |
| 30 | Silver metal (bottom) |

TO BE CONTINUED

TEST RESULT

Mechanical and Physical Properties

Test Request: As specified in Consumer Safety Specification ASTM F963-17

| Section | Description | Result |
|---------|---|--------|
| 4.1 | Material Quality | P |
| 4.3.7 | Stuffing Materials | N/A |
| 4.5 | Sound-Producing Toys | N/A |
| 4.6 | Small Objects | N/A |
| 4.6.1 | Toys that are intended for children under 36 months of age | N/A |
| 4.6.2 | Mouth-Actuated Toys | N/A |
| 4.6.3 | Toys that are intended for children over 36 months but less than 72 months | N/A |
| 4.7 | Accessible Edges | P |
| 4.8 | Projections | N/A |
| 4.8.1 | Bath Toy Projections | N/A |
| 4.9 | Accessible Points | P |
| 4.10 | Wires or Rods | N/A |
| 4.11 | Nails and Fasteners | N/A |
| 4.12 | Plastic Film | N/A |
| 4.13 | Folding Mechanisms and Hinges | N/A |
| 4.14 | Cords, Straps and Elastics | N/A |
| 4.15 | Stability and Over-Load Requirements | N/A |
| 4.16 | Confined Spaces | N/A |
| 4.17 | Wheels, Tires, and Axles | N/A |
| 4.18 | Holes, Clearances, and Accessibility of Mechanisms | P |
| 4.19 | Simulated Protective Devices | N/A |
| 4.20 | Pacifiers | N/A |
| 4.21 | Projectile Toys | N/A |
| 4.22 | Teethers and Teething Toys | N/A |
| 4.23 | Rattles | N/A |
| 4.24 | Squeeze Toys | N/A |
| 4.25 | Battery-Operated Toys (exclude section 4.25.10 Battery-powered ride-on toys and section 4.25.11 Toys contain secondary cells or secondary batteries) | N/A |
| 4.26 | Toys Intended to be Attached to a Crib or Playpen | N/A |
| 4.27 | Stuffed and Beanbag-Type Toys | N/A |
| 4.28 | Stroller and Carriage Toys | N/A |
| 4.30 | Toy Gun Marking | N/A |
| 4.31 | Balloons | N/A |
| 4.32 | Certain Toys with Nearly Spherical Ends | N/A |
| 4.33 | Marbles | N/A |
| 4.34 | Balls | N/A |
| 4.35 | Pompoms | N/A |
| 4.36 | Hemispheric-Shaped Objects | N/A |
| 4.37 | Yo Yo Elastic Tether Toys | N/A |
| 4.38 | Magnets | N/A |
| 4.39 | Jaw Entrapment in Handles and Steering Wheels | N/A |
| 4.40 | Expanding material | N/A |
| 4.41 | Toy Chests | N/A |
| 5 | Labeling Requirements | |
| 5.2 | Age Grading Labeling | P |

TEST RESULT

| Section | Description | Result |
|---------|---|--------|
| 5.3 | Safety Labeling Requirements | N/A |
| 5.4 | Aquatic Toys | N/A |
| 5.5 | Crib and Playpen Toys | N/A |
| 5.6 | Mobiles | N/A |
| 5.7 | Stroller and Carriage Toys | N/A |
| 5.8 | Toys Intended to be Assembled by an Adult | N/A |
| 5.9 | Simulated Protective Devices | N/A |
| 5.10 | Toys with Functional Sharp Edges and Sharp Points | N/A |
| 5.11 | Small Objects, Small Balls, Marbles and Balloons (16 CFR 1500.19) | N/A |
| 5.12 | Toy Caps (16 CFR 1500.86 for Required Labeling) | N/A |
| 5.13 | Art Materials (16 CFR 1500.14(b)(8)) | N/A |
| 5.14 | Electric Toys | N/A |
| 5.15 | Battery-Operated Toys | N/A |
| 5.15.1 | Battery-Powered Ride-On Toys | N/A |
| 5.15.2 | Button or Coin Cell Batteries | N/A |
| 5.16 | Promotional Materials | P |
| 5.17 | Magnets | N/A |
| 6 | Instructional Literature | |
| 6.1 | Definition and Description | N/A |
| 6.2 | Crib and Playpen Toys | N/A |
| 6.3 | Mobiles | N/A |
| 6.4 | Toys Intended to be Assembled by an Adult | N/A |
| 6.5 | Battery-Operated Toys | N/A |
| 6.6 | Battery-Powered Ride-On Toys | N/A |
| 6.7 | Toys in Contact with Food | N/A |
| 6.8 | Toy Chests | N/A |
| 7 | Producer's Markings | |
| 7.1 | Producer's or Distributor's Name and Address | P |
| 7.2 | Battery-Powered Ride-on Toys | N/A |
| 7.3 | Toy Chests | N/A |

Remark:

P – Pass

N/A – Not Applicable

TO BE CONTINUED

TEST RESULT

Flammability of Toys

Test Request: As specified in ASTM F963-17, Section 4.2, testing procedure for materials other than textiles (excluding paper) used in toys is contained in Annex A5.

| Sample | Limit | Result |
|-------------|-----------------|--------|
| Block Rocks | 0.1 inch/second | Pass |

TO BE CONTINUED

TEST RESULT

Heavy Metals

1) ASTM F963-17- Heavy Elements – Total Lead in Paint and Similar Surface-Coating Material(Clause 4.3.5.1(1))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|----------------|-------|-------|-----|--------|----|----|----|----|
| | | | | 1 | 2 | 3 | 4 | 5 |
| Total Lead | mg/kg | 90 | 10 | ND | ND | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | |
|----------------|-------|-------|-----|--------|----|
| | | | | 6 | 7 |
| Total Lead | mg/kg | 90 | 10 | 16.6 | ND |

2) ASTM F963-17- Heavy Elements – Total Lead in Substrate Material (Clause 4.3.5.2(2)(a))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|----------------|-------|-------|-----|--------|----|----|------|----|
| | | | | 8 | 9 | 10 | 11 | 12 |
| Total Lead | mg/kg | 100 | 10 | ND | ND | ND | 12.5 | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | | | |
|----------------|-------|-------|-----|--------|------|------|------|
| | | | | 27 | 28 | 29 | 30 |
| Total Lead | mg/kg | 100 | 10 | 19.6 | 22.3 | 18.3 | 18.2 |

3) ASTM F963-17- Heavy Elements – Total Elements Content, Initial Screening for Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay(Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|----------------|-------|-------|-----|--------|----|----|----|----|
| | | | | 1 | 2 | 3 | 4 | 5 |
| Total Antimony | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Arsenic | mg/kg | 25 | 5 | ND | ND | ND | ND | ND |
| Total Barium | mg/kg | 1000 | 10 | ND | ND | ND | ND | ND |
| Total Cadmium | mg/kg | 75 | 5 | ND | ND | ND | ND | ND |
| Total Chromium | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Lead | mg/kg | 90 | 10 | ND | ND | ND | ND | ND |
| Total Mercury | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Selenium | mg/kg | 500 | 10 | ND | ND | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|----------------|-------|-------|-----|--------|----|----|------|----|
| | | | | 6 | 7 | 8 | 9 | 10 |
| Total Antimony | mg/kg | 60 | 5 | 109* | ND | ND | 177* | ND |
| Total Arsenic | mg/kg | 25 | 5 | ND | ND | ND | ND | ND |
| Total Barium | mg/kg | 1000 | 10 | ND | ND | ND | ND | ND |
| Total Cadmium | mg/kg | 75 | 5 | ND | ND | ND | ND | ND |
| Total Chromium | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Lead | mg/kg | 90 | 10 | 16.6 | ND | ND | ND | ND |
| Total Mercury | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Selenium | mg/kg | 500 | 10 | ND | ND | ND | ND | ND |

TEST RESULT

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|----------------|-------|-------|-----|--------|----|----|------|------|
| | | | | 11 | 12 | 13 | 14 | 15 |
| Total Antimony | mg/kg | 60 | 5 | ND | ND | ND | 248* | 132* |
| Total Arsenic | mg/kg | 25 | 5 | ND | ND | ND | ND | ND |
| Total Barium | mg/kg | 1000 | 10 | ND | ND | ND | ND | ND |
| Total Cadmium | mg/kg | 75 | 5 | ND | ND | ND | 144* | ND |
| Total Chromium | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Lead | mg/kg | 90 | 10 | 12.5 | ND | ND | ND | ND |
| Total Mercury | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Selenium | mg/kg | 500 | 10 | ND | ND | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|----------------|-------|-------|-----|--------|----|------|------|------|
| | | | | 16 | 17 | 18 | 19 | 20 |
| Total Antimony | mg/kg | 60 | 5 | 189* | ND | 143* | 138* | 172* |
| Total Arsenic | mg/kg | 25 | 5 | ND | ND | ND | ND | ND |
| Total Barium | mg/kg | 1000 | 10 | ND | ND | ND | ND | ND |
| Total Cadmium | mg/kg | 75 | 5 | ND | ND | ND | 52.5 | 67.9 |
| Total Chromium | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Lead | mg/kg | 90 | 10 | ND | ND | ND | ND | ND |
| Total Mercury | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Selenium | mg/kg | 500 | 10 | ND | ND | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|----------------|-------|-------|-----|--------|------|------|------|-------|
| | | | | 21 | 22 | 23 | 24 | 25 |
| Total Antimony | mg/kg | 60 | 5 | 166* | 158* | 109* | 157* | 165* |
| Total Arsenic | mg/kg | 25 | 5 | ND | ND | ND | ND | ND |
| Total Barium | mg/kg | 1000 | 10 | ND | ND | ND | ND | ND |
| Total Cadmium | mg/kg | 75 | 5 | 70.4 | 63.6 | 55.7 | 61.4 | 78.8* |
| Total Chromium | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Lead | mg/kg | 90 | 10 | ND | ND | ND | ND | ND |
| Total Mercury | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Total Selenium | mg/kg | 500 | 10 | ND | ND | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result |
|----------------|-------|-------|-----|--------|
| | | | | 26 |
| Total Antimony | mg/kg | 60 | 5 | ND |
| Total Arsenic | mg/kg | 25 | 5 | ND |
| Total Barium | mg/kg | 1000 | 10 | ND |
| Total Cadmium | mg/kg | 75 | 5 | ND |
| Total Chromium | mg/kg | 60 | 5 | ND |
| Total Lead | mg/kg | 90 | 10 | ND |
| Total Mercury | mg/kg | 60 | 5 | ND |
| Total Selenium | mg/kg | 500 | 10 | ND |

TO BE CONTINUED

TEST RESULT

4) ASTM F963-17- Heavy Elements – Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay (Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.2 to 8.3.5 (excluding 8.3.5.5(3))

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|------------------|-------|-------|-----|--------|----|------|----|----|
| | | | | 6 | 9 | 14 | 15 | 16 |
| Soluble Antimony | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Soluble Arsenic | mg/kg | 25 | 5 | ND | ND | ND | ND | ND |
| Soluble Barium | mg/kg | 1000 | 10 | ND | ND | 30.0 | ND | ND |
| Soluble Cadmium | mg/kg | 75 | 5 | ND | ND | 14.1 | ND | ND |
| Soluble Chromium | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Soluble Lead | mg/kg | 90 | 10 | ND | ND | ND | ND | ND |
| Soluble Mercury | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Soluble Selenium | mg/kg | 500 | 10 | ND | ND | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | | | | |
|------------------|-------|-------|-----|--------|----|----|----|----|
| | | | | 18 | 19 | 20 | 21 | 22 |
| Soluble Antimony | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Soluble Arsenic | mg/kg | 25 | 5 | ND | ND | ND | ND | ND |
| Soluble Barium | mg/kg | 1000 | 10 | ND | ND | ND | ND | ND |
| Soluble Cadmium | mg/kg | 75 | 5 | ND | ND | ND | ND | ND |
| Soluble Chromium | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Soluble Lead | mg/kg | 90 | 10 | ND | ND | ND | ND | ND |
| Soluble Mercury | mg/kg | 60 | 5 | ND | ND | ND | ND | ND |
| Soluble Selenium | mg/kg | 500 | 10 | ND | ND | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | | |
|------------------|-------|-------|-----|--------|----|----|
| | | | | 23 | 24 | 25 |
| Soluble Antimony | mg/kg | 60 | 5 | ND | ND | ND |
| Soluble Arsenic | mg/kg | 25 | 5 | ND | ND | ND |
| Soluble Barium | mg/kg | 1000 | 10 | ND | ND | ND |
| Soluble Cadmium | mg/kg | 75 | 5 | ND | ND | ND |
| Soluble Chromium | mg/kg | 60 | 5 | ND | ND | ND |
| Soluble Lead | mg/kg | 90 | 10 | ND | ND | ND |
| Soluble Mercury | mg/kg | 60 | 5 | ND | ND | ND |
| Soluble Selenium | mg/kg | 500 | 10 | ND | ND | ND |

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

The analytical results were adjusted by subtracting analytical correction factor.

* On the initial analysis for soluble heavy metals content, any tested component of greater than the set limit, the result is inconclusive for the requirement and therefore were retested with soluble heavy metals analysis of ASTM F963-17, Sections 8.3.2 to 8.3.5 as specified in Section 8.3.1.3. The result herein is for reference only (show data), please refer to soluble heavy metals content analysis for the corresponding conclusive results.

TO BE CONTINUED

TEST RESULT

Total Lead Content in Paint / Surface Coating

Test Request: Total lead in paint/ similar surface coatings as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1003-09.1
The sample was acid digested, and total lead content was determined by ICP-OES.

| Tested Item(s) | Unit | Limit | MDL | Result | | |
|----------------|-------|-------|-----|--------|-------|----|
| | | | | 1+2+3 | 4+5+6 | 7 |
| Total Lead(Pb) | mg/kg | 90 | 10 | ND | ND | ND |

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

TO BE CONTINUED

TEST RESULT

Total Lead Content in Substrate

Test Request: Total lead in substrate as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1001-08.3, CPSC-CH-E1002-08.3
The sample was acid digested, and total lead content was determined by ICP-OES.

| Tested Item(s) | Unit | Limit | MDL | Result | | | |
|----------------|-------|-------|-----|--------|----|------|----|
| | | | | 8+9 | 10 | 11 | 12 |
| Total Lead(Pb) | mg/kg | 100 | 10 | ND | ND | 12.5 | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | |
|----------------|-------|-------|-----|----------|------|
| | | | | 27+28+29 | 30 |
| Total Lead(Pb) | mg/kg | 100 | 10 | 20.1 | 18.2 |

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

TO BE CONTINUED

TEST RESULT

Total Lead Content

Test Request: Total lead content as specified in US California Proposition 65
 Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996
 Acid digestion/ microwave digestion method was used and total lead content was determined by ICP-OES.

| Tested Item(s) | Unit | Limit | MDL | Result | | |
|----------------|-------|-------|-----|--------|-------|----|
| | | | | 1+2+3 | 4+5+6 | 7 |
| Total Lead(Pb) | mg/kg | 90 | 10 | ND | ND | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | | | |
|----------------|-------|-------|-----|--------|----|------|----|
| | | | | 8+9 | 10 | 11 | 12 |
| Total Lead(Pb) | mg/kg | 100 | 10 | ND | ND | 12.5 | ND |

| Tested Item(s) | Unit | Limit | MDL | Result | |
|----------------|-------|-------|-----|----------|------|
| | | | | 27+28+29 | 30 |
| Total Lead(Pb) | mg/kg | 100 | 10 | 20.1 | 18.2 |

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

The limit(s) was/were referred from various court cases.

Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 108

Test Method: CPSC-CH-C1001-09.3

| Tested Item(s) | CAS No. | Unit | Limit | MDL | Result | | | |
|---|------------|------|-------|-------|--------|-------|-------|-----|
| | | | | | 1+2+3 | 4+5+6 | 7 | 8+9 |
| For toys and childcare articles | | | | | | | | |
| Dibutylphthalate (DBP) | 84-74-2 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Di-2-ethylhexylphthalate (DEHP) | 117-81-7 | % | 0.1 | 0.005 | ND | ND | 0.009 | ND |
| Benzylbutylphthalate (BBP) | 85-68-7 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Additional requirements for toys and childcare articles, which can be placed in the mouth by children | | | | | | | | |
| Diisononyl phthalate (DINP) | 68515-48-0 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Di-n-octylphthalate (DNOP) | 117-84-0 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Di-iso-decylphthalate (DIDP) | 26761-40-0 | % | 0.1 | 0.005 | ND | ND | ND | ND |

| Tested Item(s) | CAS No. | Unit | Limit | MDL | Result | | |
|---|------------|------|-------|-------|--------|-------|-------|
| | | | | | 10 | 11 | 12 |
| For toys and childcare articles | | | | | | | |
| Dibutylphthalate (DBP) | 84-74-2 | % | 0.1 | 0.005 | ND | ND | ND |
| Di-2-ethylhexylphthalate (DEHP) | 117-81-7 | % | 0.1 | 0.005 | ND | 0.035 | 0.023 |
| Benzylbutylphthalate (BBP) | 85-68-7 | % | 0.1 | 0.005 | ND | ND | ND |
| Additional requirements for toys and childcare articles, which can be placed in the mouth by children | | | | | | | |
| Diisononyl phthalate (DINP) | 68515-48-0 | % | 0.1 | 0.005 | ND | 0.019 | 0.022 |
| Di-n-octylphthalate (DNOP) | 117-84-0 | % | 0.1 | 0.005 | ND | ND | ND |
| Di-iso-decylphthalate (DIDP) | 26761-40-0 | % | 0.1 | 0.005 | ND | ND | ND |

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates Content as specified in US California Proposition 65

Test Method: EPA 3550C:2007, EPA 8270D:2014, solvent extraction and quantification by GC-MS.

| Tested Item(s) | CAS No. | Unit | Limit | MDL | Result | | | |
|------------------------------|------------|------|-------|-------|--------|-------|-------|-----|
| | | | | | 1+2+3 | 4+5+6 | 7 | 8+9 |
| Dibutylphthalate (DBP) | 84-74-2 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Benzylbutylphthalate (BBP) | 85-68-7 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Diethylhexylphthalate (DEHP) | 117-81-7 | % | 0.1 | 0.005 | ND | ND | 0.009 | ND |
| Diisononylphthalate (DINP) | 28553-12-0 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Diisodecylphthalate (DIDP) | 26761-40-0 | % | 0.1 | 0.005 | ND | ND | ND | ND |
| Di-n-hexyl phthalate (DnHP) | 84-75-3 | % | 0.1 | 0.005 | ND | ND | ND | ND |

| Tested Item(s) | CAS No. | Unit | Limit | MDL | Result | | |
|------------------------------|------------|------|-------|-------|--------|-------|-------|
| | | | | | 10 | 11 | 12 |
| Dibutylphthalate (DBP) | 84-74-2 | % | 0.1 | 0.005 | ND | ND | ND |
| Benzylbutylphthalate (BBP) | 85-68-7 | % | 0.1 | 0.005 | ND | ND | ND |
| Diethylhexylphthalate (DEHP) | 117-81-7 | % | 0.1 | 0.005 | ND | 0.035 | 0.023 |
| Diisononylphthalate (DINP) | 28553-12-0 | % | 0.1 | 0.005 | ND | 0.019 | 0.022 |
| Diisodecylphthalate (DIDP) | 26761-40-0 | % | 0.1 | 0.005 | ND | ND | ND |
| Di-n-hexyl phthalate (DnHP) | 84-75-3 | % | 0.1 | 0.005 | ND | ND | ND |

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

The limit(s) was/were referred from various court cases.

Compliance with the above stated limit(s) does not show compliance with Proposition 65 or a guarantee against possible legal action but provides a relative level of assurance against potential lawsuits.

END OF THE REPORT